



**Tetcon Global bv**  
**Tarasconweg 13**  
**5627 GB EINDHOVEN**  
**Netherlands**

**Your notice of**  
12-03-2026

**Your reference**

**Date**  
10-04-2026

## Analysis Report 26.01355.01


Required tests :  
**BS 7175 (1989)**

**Section 2 – Pillows and continental quilts - Ignitability by a smouldering cigarette**

Sample id	Information given by the client	Date of receipt
T2605146	Tricot Extreme Pillow Navy Blue (3014NAVY00)	12-03-2026

Gina Créelle  
Order responsible


This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.  
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.  
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.



### Samples

T2605146  
Tricot Extreme Pillow Navy  
Blue (3014NAVY00)





**Reference: T2605146 - Tricot Extreme Pillow Navy Blue (3014NAVY00)**

**Section 2 – Pillows and continental quilts - Ignitability by a smouldering cigarette**

Date of ending the test 09-04-2026  
 Standard used BS 7175 (1989)  
 Deviation from the standard -  
 Conditioning 20°C, relative humidity 65%

The following test results relate only to the ignitability of the combination of materials under the particular conditions of test ; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

Specimen \* Pillow  
 \* Information given by the client  
 Testing substrate Mineral wool fibre pad

Cigarette placed on top surface

	1	2
<b>Smouldering criteria</b>		
Unsafe escalating combustion	no	no
Test assembly consumed	no	no
Smoke/heat/glowing more than 60 min	no	no
Final examination / active smouldering	no	no
<b>Flaming criteria</b>		
Occurrence of flames	no	no
Conclusion	<b>non-ignition</b>	<b>non-ignition</b>



Cigarette placed at the junction between the testing substrate and the specimen

	1	2
<b>Smouldering criteria</b>		
Unsafe escalating combustion	no	no
Test assembly consumed	no	no
Smoke/heat/glowing more than 60 min	no	no
Final examination / active smouldering	no	no
<b>Flaming criteria</b>		
Occurrence of flames	no	no
Conclusion	<b>non-ignition</b>	<b>non-ignition</b>

**Conclusion**

**Non-ignition**